

Style Elle xf² (2.5mm)

Datasheet

Classification	Norm	Tarkett Value
Product type	ISO 24011	Plain and decorative linoleum
Domestic classification	EN ISO 10874	23 Heavy
Commercial classification	EN ISO 10874	34 Very Heavy
Industrial classification	EN ISO 10874	43 Heavy
Technical Characteristics	Norm	Tarkett Value
Surface treatment		xf ² ™
Total thickness	ISO 24346	2,50 mm
Total weight	ISO 23997	2900 g/m ²
Flexibility	ISO 24344 Method A	≤ 30 mm ø Average measured value : 17,5 mm ø
Performance for CE Marking	Norm	Tarkett Value
CE Marking	EN 14041	EN 14041
Declaration of Performance #	EN 14041	0200 0001 DoP 2013 07
Reaction to fire - Glued on non-combustible substrate	EN 13501-1	Cfl-s1
Slip resistance (DIN 51130)	DIN 51130	R9
Slip resistance (EN 13893)	EN 13893	Class DS (μ ≥ 0,30)
Static Electrical Propensity	EN 1815	Antistatic (≤ 2 kV)
Technical Performance	Norm	Tarkett Value
Residual indentation	EN ISO 24343-1	≤ 0,15 mm Average measured value: ca. 0,08 mm
Impact sound reduction - ΔLw	EN ISO 10140-3 / 717-2	6 dB
Reduction of in-room impact noise	NF S31-074	Class C (≤ 85 dB)
Castor chair	EN ISO 4918	Suitable for office chairs with castors type W (Norm EN 12529)
Chemical resistance	ISO 26987	Resistant to dilute acids, oils, fats, current solvents and alkalis
Underfloor heating		Suitable (subfloor temperature maximum 27°C)
Light fastness	ISO 105-B02	≥ 6
Determination of antibacterial activity	ISO 22196	Naturally antibacterial (Bacteria mix - Ecoli and MRSA)
Sustainability performances	Norm	Tarkett Value
Recyclability through ReStart®		Offcuts / Post-use - Contact Tarkett for more information
Carbon Footprint (Cradle-to-Gate, EPD Modules A1-A3)		-0,60 kg CO ₂ eq /m ²
Recycled content		36 %
Total VOC Emissions (after 28 days)	EN 16516	Platinum (≤ 10 μg/m ³)
Dimensions and designs		
Roll		Roll 2 x ≤32m
Number of designs available		6

Impact sound reduction with Elafono* - ΔLw (EN ISO 10140-3 / 717-2) : 14dB

*Elafono : 2,0mm traditional, 100% natural corkment underlay to be installed in combination with any compact Tarkett linoleum to get additional sound reduction (up to 15dB, depending on the product).



The above information is subject to modification for the benefit of further improvement (10/06/2025). According to the European Regulation N°305/2011 for CE Marking, the Declarations of Performance are available on our website <https://www.tarkett.com>. Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for the instructions.