

XIAMEN NOYA MANUFACTURING&TRADING CO., LTD.

ADD.: 2L, XINGHU BUILDING, NO.46 HULI ROAD, XIAMEN, CHINA

Tel.: +86-592-5685666

Fax: +86-592-3761616 Email: noya2@noya.cn

CERAMIC FIBER BLANKET

Regular Size (mm) 14000x610x13mm,7200x610x25mm,3600x610x50mm

Item/Type		Standard
Classification Temperature (°C)		1260
Working temperature (°C)		1050
Color		Pure white
Density (kg/m ³)		128
Permanent linear shrinkage (%) (24H, 128kg/m ³)		≦4.00
Heat conductivity (w/m.k)Average temperature 500°C		≦0.156
Compressive strength (Mpa) (Thickness direction shrink 10%)		0.5
Tensile strength Kpa		≧30.00
Shot content >0.21mm		≦20.00
Chemical composition (%)	AL2O3	43
	SI02	≦55
	Zro2	-
	Fe2o3	<1.0
	Na2O+K2O	≦0.50